

Cosmetic compositions are provided containing vinyl-silicone graft or block copolymers of the formula (I).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

- 1 -

Polymers in Cosmetics and Personal Care ProductsTechnical Field

5 The present invention relates to cosmetic compositions. More specifically, the present invention relates to cosmetic compositions containing a vinyl-silicone graft or block copolymer.

10 Background Art

 Cosmetics are applied to skin, hair, teeth, and nails for the purpose of cleansing, and/or protecting these personal surfaces from noxious external influences, and to provide visual appeal to
15 these surfaces. Keeping the body clean is surely the first and most primitive demand of personal hygiene and, therefore, one of the main purposes of cosmetics. Another purpose is to protect such personal surfaces. Cleansers protect the skin by removing impurities.
20 Disinfectants protect the skin by destroying noxious bacteria and fungi. Other preparations act prophylactically by isolating the skin from contact with harmful external agents.

 Typical skin protectors are applied before
25 skin is exposed to harmful external agents. Ideally, such protectors act as an invisible sheath completely impenetrable to harmful agents or even deliver ingredients that kill harmful bacteria. Skin protectors can be differentiated according to their
30 specific purposes, e.g., protection against chemical agents (caustic chemicals, detergent solutions, etc.); protection against dust and soil, tar, and lubricants; protection against physical agents (ultraviolet rays and heat); protection against mechanical injuries
35 (lubricant and massage preparations) and insect repellents.

 In addition to the above discussed purposes

- 2 -

of basic cosmetics, the suppression of body odor or personal wetness is also a very important part of personal hygiene and therefor also a basic cosmetic function. Specific examples of such basic cosmetics are, e.g., soaps, detergents, cleansing lotions and the like for skin cleaning; shampoos, conditioners and the like for hair cleaning and protecting; toothpastes, tooth creams, and the like for oral hygiene; creams, emulsions, sunscreen preparations, sunburn preventive preparations, lubricating and massaging preparations, insect repellent preparations and the like to protect the skin from harmful effects of either chemicals, dust and soil, ultraviolet rays, insects, and other harmful agents present in the environment. Antiperspirant, foot deodorants, mouthwashes, and the like to improve or eliminate odors or personal wetness by eliminating bacterial actions, and/or retention of medicament on a surface are also within this category of basic cosmetic.

Another category of cosmetics is the "decorative products." Decorative products relate to the health of the skin only to the extent that they must damage it as little as possible. These products are used to hide small blemishes or symptoms of aging. They are also used to create a well-groomed appearance and to demonstrate the desire not to create a bad impression on the outside world. Decorative cosmetics may consist in surface measures, in which the preparation is applied to the surface of skin, nails, or hair, or in permanent measures that cannot be canceled by simple countermeasures. Their sole purpose is an alteration of the appearance, for example, preparation for coloring skin and nails, preparation for masking skin imperfections and shininess, hair grooming aids with and without lasting effects, and the like. Specific examples of decorative cosmetics useful to be applied to the face, also known as makeup

- 3 -

cosmetics, include foundation, lipsticks, rouges, eyeliners, mascara, eyeshadows, eyebrow pencils, manicures, face powders, and the like. Cosmetics useful for application to the hair include hair oils, 5 hair creams, hair lacquers, hair lotions, hair dyes and bleaches, permanent wave solutions, and the like. Skin-bleaching preparations, and hair-removal preparations are also considered decorative cosmetics because of their role in enhancing the appearance of 10 the skin.

U.S. Pat. No. 3,563,941 to Plueddemann, published February 16, 1971, discloses the preparation of silicone modified carnauba wax which is useful in cosmetic compositions. U.S. Pat. No. 3,641,239 to 15 Mohrlok, issued February 8, 1972, discloses the use of silicone wax in cosmetic formulations such as lipsticks. Silicone waxes, as defined, are organosiloxane copolymers containing carnauba wax, hydrocarbon, phenyl, or silphenylene groups in the 20 silicone chain.

U.S. Pat. No. 4,268,499 to Keil, issued May 19, 1981, discloses antiperspirant emulsions containing polydiorganosiloxanes-polyoxyalkylene copolymers as well as volatile silicones. U.S. Pat. 25 No. 4,532,132 to Keil, published July 30, 1985, and U.S. Pat. No. 4,311,695 to Starch, published January 19, 1982, disclose the use of organosiloxane-polyoxyalkylene copolymers in skin care/personal care products.

30 Siloxanes (see, for example, U.S. Pat. No. 3,208,911 to Opplinger, issued September 28, 1965) and siloxane-containing polymers have been taught also for their use in hair conditioning compositions. U.S. Pat. No. 4,902,499 to Bolich, Jr., et al., issued February 35 20, 1990, describes the use of rigid silicone polymers in hair care compositions. U.S. Pat. No. 4,971,786 to Grollier et al., issued November 20, 1990, describes

- 4 -

the use of ethoxylated copolymer of dimethylsiloxane/3-hydroxy-propylmethethylsiloxane in hair conditioning or shampoo/conditioner compositions. U.S. Patent 4,839,167 to Yamamoto et al. issued June 13, 1989, and

5 U.S. Pat. No. 3,928,558 to Cheesman et al., issued December 23, 1975, describes the use of a mixture of polyethersiloxane copolymers with a surfactant and water or water/ethanol soluble polymer in hair care application. U.S. Pat. No. 4,654,161 to Kollmeier et

10 al., issued March 31, 1987, describes organopoly-siloxanes containing betaine substituents. When used in hair care compositions, these compounds are said to provide good conditioning, compatibility with anionic components, hair substantivity, and low skin

15 irritation. U.S. Pat. No. 4,563,347 to Starch, issued January 7, 1986, relates to hair conditioning compositions which include siloxane components containing substituents to provide attachment to hair. Japanese Published Application 56-129,300 to Lion

20 Corporation, published October 9, 1981, relates to shampoo conditioner compositions which include an organopolysiloxane oxyalkylene copolymer together with an acrylic resin. U.S. Pat. No. 4,185,087 to Morlino, issued January 22, 1980, describes quaternary nitrogen

25 derivatives of trialkylamino hydroxy organosilicon compounds which are said to have superior hair conditioning properties. U.S. Pat. No. 4,479,893 to Hirota et al., issued October 30, 1984, describes shampoo/conditioner compositions containing a phosphate

30 ester surfactant and a silicon derivative (e.g., polyether- or alcohol-modified). Polyether-modified polysiloxanes are also disclosed for use in shampoos in U.S. Pat. No. 3,957,970 to Korkis, issued May 18, 1976.

Siloxane-derived materials have also been

35 used in hair styling compositions. U.S. Pat. No. 4,744,978 to Homan et al., issued May 17, 1988, describes hair styling compositions (such as hair

- 5 -

- sprays) which include the combination of a carboxy functional polydimethylsiloxane and a cationic organic polymer containing amine or ammonium groups. Hair styling compositions which include
- 5 polydiorganosiloxanes and a cationic organic polymer are taught in U.S. Pat. No. 4,733,677 to Gee et al., issued March 29, 1988, and U.S. Pat. No. 4,724,851 to Cornwall et al., issued February 16, 1988. Japanese Published Application 56-092,811 to Lion Corporation,
- 10 published December 27, 1979, describes hair setting composition which comprises an amphoteric acrylic resin, a polyoxyalkylene-denatured organopolysiloxane, and polyethylene glycol. European Patent Application 117,360 to Cantrell et al., published September 5,
- 15 1984, discloses compositions, containing a siloxane polymer having at least one nitrogen-hydrogen bond, a surfactant, and a solubilized titanate, zirconate or germanate, which act as both a conditioner and a hair styling aid.
- 20 European Patent Application 412,704 to Bolich et al., published February 13, 1991, European Patent Application 408,311 to Kawaguchi et al., published January 16, 1991, and European Patent Application 412,707 to Torgerson et al., published February 13,
- 25 1991, have suggested the use of silicone grafted acrylate copolymers in hair care application. U.S. Pat. No. 4,988,506 to Mitra et al., issued January 29, 1991, describes the use of non-pressure sensitive polysiloxane-grafted copolymers in hair care
- 30 compositions.
- U.S. Pat. No. 5,061,481 to Suzuki et al., published October 29, 1991, has disclosed the use of acryl-silicone graft copolymers in cosmetic compositions. These copolymers are prepared by the
- 35 free radical polymerization of (meth)acrylate monomers with mono (meth)acrylate terminated polydiorganosiloxanes, thereby giving a copolymer which

- 6 -

has a (meth)acrylate backbone with polydiorganosiloxane chain grafted to it. Polydiorganosiloxanes, being of high molecular weight, generally do not react completely. Thus the copolymers prepared by the above disclosed method contain ungrafted polydiorganosiloxane. Presence of free polydiorganosiloxane and a silicone free polymer leads to either insolubility in desired solvents such as low boiling-point silicone oils such as polydimethylsiloxane with a low degree of polymerization, octamethylcyclo-tetrasiloxane (D_4), decamethylcyclopentasiloxane (D_5), phenylpentamethyldisiloxane, and phenethylpentamethyldisiloxane, and the like. Poor incorporation of silicone macromer into the copolymer also leads to adverse effects on the desired properties of cosmetics. In addition, silicone macromer, which is prepared by anionic polymerization of hexamethyltrisiloxane (D_3), is available only from limited number of sources and is an expensive commodity.

U.S. Pat. No. 5,032,460 to Kantner et al., published July 16, 1991, assigned to the present assignee, has disclosed the preparation of vinyl-silicone copolymers which involve the use of a mercapto functional silicone compound as a chain transfer agent and their use as release coatings for various pressure sensitive adhesives. U.S. Pat. No. 4,987,180 to Saga et al., published January 22, 1991, has disclosed the preparation of vinyl-silicone copolymers utilizing emulsion polymerization method and their use as fabric finishing agents. These copolymers comprise a silicone backbone with an acrylate chain grafted to it, i.e. the reverse molecular arrangement than that disclosed above in E.P. Applications 412,704; E.P. Application 408,311; E.P. Application 412,707, and U.S. Pat. No. 5,061,481. The copolymers disclosed in U.S. Pat. No. 5,032,460 and 4,987,180 are prepared by the free radical

- 7 -

polymerization of ethylenically unsaturated monomers with a mercapto functional silicone as a chain transfer agent. A number of references disclosed in U.S. Pat. No. 5,032,460 describe the preparation of mercapto functional silicone compounds.

Disclosure of Invention

A need exists for conveniently prepared and cost-effective polymers for use in cosmetic compositions. In the case of conventional makeup cosmetics, the composition should give a good sensation upon use, and should produce a cosmetic film that is sufficiently water resistant and friction resistant. In the case of personal care products for use in oral hygiene, the composition should provide a smooth, thin coating on teeth that prevents the adherence of bacteria to these surfaces. In the case of hair care compositions, the composition should provide excellent brilliance, gloss, conditioning and style retention to hair without stiff or sticky feel. In the case of moisturizers or other skin treatments, the composition should provide moisture-retaining properties by retarding evaporation of moisture through the skin, and should provide superior water and oil repellency and retentiveness of the makeup.

The present invention relates to cosmetics and personal care compositions containing a vinyl-silicone graft or block copolymer comprising a silicone polymer segment and a vinyl polymer segment. This block or graft copolymer is prepared by the free radical polymerization of a mercapto functional silicone chain transfer agent and vinyl monomers.


Compositions according to the present invention are effective moisture barriers and help retain the natural moisture of the skin. They also provide good sensation upon use, along with superior water-repellency, oil-resistance and good retentiveness

- 8 -

of the makeup when used in cosmetics, such as foundation, lipsticks, rouges, and the like. In case of personal hygiene, and personal care products, such as, anti-perspirants, deodorants, tooth paste, and the like, these polymers provide a smooth, water-resistant film which prevents the growth of bacteria. When used in hair care cosmetic formulations, these polymers provide excellent brilliance, gloss, conditioning, and style retention properties without a stiff, and sticky feel.

Detailed Description

The copolymer used in the compositions of the present invention is either a graft or block copolymer and is represented by the following general formula.



wherein G_5 represent monovalent moieties which can independently be the same or different selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, fluoroalkyl, hydrogen, and -ZSA; A represents a vinyl polymeric segment consisting essentially of polymerized free radically polymerizable monomer, and Z is a divalent linking group. Useful divalent linking groups Z include but are not limited to the following: C_1 to C_{10} alkylene, alkarylene, arylene, and alkoxyalkylene. Preferably, Z is selected from the groups consisting of methylene and propylene for reasons of commercial availability.

G_6 represents monovalent moieties which can independently be the same or different selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, fluoroalkyl, hydrogen, and -ZSA;


- 9 -

G₂ comprises A;

G₄ comprises A;

R₁ represents monovalent moieties which can
5 independently be the same or different and are selected
from the group consisting of alkyl, aryl, alkaryl,
alkoxy, alkylamino, fluoroalkyl, hydrogen, and
hydroxyl; Preferably, R₁ represents monovalent moieties
which can independently be the same or different
10 selected from the group consisting of C₁₋₄ alkyl and
hydroxyl for reasons of commercial availability. Most
preferably, R₁ is methyl.

R₂ can independently be the same or different
and represents divalent linking groups. Suitable
15 divalent linking groups include but are not limited to
the following: C₁ to C₁₀ alkylene, arylene, alkarylene,
and alkoxyalkylene. Preferably, R₂ is selected from the
group consisting of C₁₋₃ alkylene and C₇₋₁₀ alkarylene due
to ease of synthesis of the compound. Most preferably,
20 R₂ is selected from the group consisting of -CH₂-,
1,3-propylene, and



25


R₃ represents monovalent moieties which can
independently be the same or different and are selected
from the group consisting of alkyl, aryl, alkaryl,
30 alkoxy, alkylamino, fluoroalkyl, hydrogen, and
hydroxyl; Preferably, R₃ represents monovalent moieties
which can independently be the same or different
selected from the group consisting of C₁₋₄ alkyl and
hydroxyl for reasons of commercial availability. Most
35 preferably, R₃ is methyl.

R₄ can independently be the same or different
and are divalent linking groups. Suitable divalent

- 10 -

linking groups include but are not limited to the following: C_1 to C_{10} alkylene, arylene, alkarylene and alkoxyalkylene. Preferably, R_4 is selected from the group consisting of C_{1-3} alkylene and C_7-C_{10} alkarylene for reasons of ease of synthesis. Most preferably, R_4 is selected from the group consisting of $-CH_2-$, 1,3-propylene, and

10



x is an integer of 0-3;

y is an integer of 5 or greater; preferably, y is an integer ranging from about 10 to about 270 in order to provide the silicone segment with a molecular weight ranging from about 750 to about 20,000. Most preferably, y is an integer ranging from about 40 to about 270;

q is an integer of 0-3;

wherein at least one of the following is true:

q is an integer of at least 1;

x is an integer of at least 1;

G_5 comprises at least one -ZSA moiety;

G_6 comprises at least one -ZSA moiety.

As noted above, A is a vinyl polymeric segment formed from polymerized free radically polymerizable monomers. The selection of A is typically based upon the intended uses of the composition, and the properties the copolymer must possess in order to accomplish its intended purpose. If A comprises a block in the case of block copolymers, a polymer having AB and ABA architecture will be obtained depending upon whether a mercapto functional group $-SH$ is attached to one or both terminal silicon atoms of the mercapto functional silicone compounds,

- 11 -

respectively. The weight ratio of vinyl polymer block or segment, to silicone segment of the copolymer can vary. The preferred copolymers are those wherein the weight ratio of vinyl polymer segment to silicone
5 segment ranges from about 98:2 to 40:60, in order that the copolymer possesses properties inherent to each of the different polymeric segment while retaining the overall polymer's solubility in low-viscosity silicone oil and/or low-boiling-point oil.

10

A Segment Monomeric Components

Representative examples of monomers that may be used to form the vinyl polymeric segment represented herein by A (hereafter "A monomers") are the lower to
15 intermediate acrylic acid esters, or methacrylic acid esters of alkyl alcohols. Specific examples of such alcohols include methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, 1,1-dimethyl ethanol, 2-methyl-1-propanol, 1-pentanol, 2-pentanol,
20 3-pentanol, 2-methyl-1-butanol, 3-methyl-1-butanol, 2-hexanol, 3-methyl-1-pentanol, 3-methyl-1-pentanol, cyclohexanol, 2-ethyl-1-butanol, 3-heptanol, benzyl alcohol, 2-octanol, 6-methyl-1-heptanol, 2-ethyl-1-hexanol, 3,5-dimethyl-1-hexanol, 3,5,5-trimethyl-1-
25 hexanol, 1-decanol, and 1-dodecanol, and the like. Preferably, the alcohols have from 1 to 18 carbon atoms, and more preferably 1 to 12 carbon atoms, with the average number of carbon atoms being about 4 to 18. Some small amount of copolymerizable styrene, vinyl
30 esters, vinyl chloride, vinylidene chloride, acrylonitrile, methacrylonitrile, acryloxypropyl tri-methoxysilane, methacryloxypropyl tri-methoxysilane, other acryloyl monomers and the like may be used. Such monomers are known in the art and
35 many are commercially available. Particularly preferred monomers include isooctyl(meth)acrylate, isononyl (meth)acrylate 2-ethylhexyl (meth)acrylate,

- 12 -

lauryl (meth)acrylate i-pentyl (meth)acrylate, n-butyl (meth)acrylate, i-butyl (meth)acrylate, methyl (meth)acrylate, ethyl (meth)acrylate, t-butyl(meth)acrylate, tridecyl (meth)acrylate, stearyl (meth)acrylate, etc., and mixtures thereof with above defined monomers.


Representative examples of polar monomers useful as A monomers include hydrophilic unsaturated monomers of a cationic, anionic, nonionic, or amphoteric nature which are polymerizable through radical polymerization. Examples of such polar monomers include acrylic acid, methacrylic acid, itaconic acid, vinyl acetic acid, acrylonitrile, fumaric acid, maleic acid, maleic anhydride, crotonic acid, acrylamide, vinyl pyridine, vinyl pyrrolidone, N,N-dimethylacrylamide, N-t-butylacrylamide, methacrylonitrile, and the like.

A monomers can also be half esters of an unsaturated polybasic acid anhydride such as succinic anhydride, phthalic anhydride, 4-methacryloxyethyl-trimellitic anhydride (4-META) or the like with a hydroxyl group containing (meth)acrylates such as hydroxy ethyl (meth)acrylate, hydroxy propyl (meth)acrylate or the like. In addition, polymeric monomers or macromonomers, as defined hereinafter, are also useful as monomers. Representative examples of such polymeric monomers are poly(styrene), poly(α -methyl styrene), poly(vinyl toluene), polymethyl (meth)acrylate, and poly(oxyalkylene) macromonomers.

Preferred representative examples also include highly polar acrylic and methacrylic monomers. A highly polar monomer as defined herein are acrylic or methacrylic monomers having at least one highly polarizing group such as hydroxyl (OH), alkoxy, amino (primary, secondary, and tertiary), ionic groups (e.g., quaternary ammonium, carboxylate salt, sulfonic acid salt, etc.), and alkenyl heterocycles.

- 13 -


In the case of hydroxyl-containing monomers, such monomers may be more specifically represented by the general formula:



where $\text{R}^2 = \text{H}$, methyl, ethyl, cyano or carboxymethyl, $\text{L} = -\text{O}$, $-\text{NH}$, $d = 1-3$ and R^3 is a hydrocarbyl radical of valence $d+1$ containing from 1 to 12 carbon atoms. The preferred monomers in this class are hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, hydroxybutyl (meth)acrylate, glycerol mono(meth)acrylate, tris(hydroxymethyl) ethane monoacrylate, pentaerythritol mono(meth)acrylate. N-hydroxymethyl (meth)acrylamide, hydroxyethyl (meth)acrylamide and hydroxypropyl (meth)acrylamide.

The highly polar monomers may also be alkoxy substituted (meth)acrylates or (meth)acrylamides such as methoxyethyl (meth)acrylate, 2(2-ethoxyethoxy)ethyl (meth)acrylate, polyethylene glycol mono(meth)acrylate or polypropylene glycol mono(meth)acrylate.

Amino groups containing highly polar monomers may be represented by the general formula:




where R^2 , L , R^3 , and d are as defined above and R^4 and R^5 are H or alkyl groups of 1 to 12 carbon atoms or together they constitute a carbocyclic or heterocyclic group. Preferred monomers of this class are aminoethyl (meth)acrylate, aminopropyl (meth)acrylate, N,N-dimethylaminoethyl (meth)acrylate, N,N-diethylamino-ethyl (meth)acrylate, N,N-dimethylaminopropyl (meth)acrylamide, N-isopropylaminopropyl (meth)acrylamide, and 4-methyl-1-acryloyl-piperazine.

Monomers that have substituted or unsubstituted ammonium groups may be represented by the

- 14 -

general formula:



where R^2 , R^3 , R^4 , R^5 , L , and d are as defined above, and where R^6 is H or alkyl group of 1-12 carbon atoms and Q^- is an organic or inorganic anion. Preferred examples
 10 of such monomers are 2-N,N,N-trimethylammoniummethyl (meth)acrylate, 2-N,N,N-triethylammonium ethyl (meth)acrylate, 3-N,N,N-triethylammonium propyl (meth)acrylate, N(2-N',N',N'-trimethylammonium) ethyl (meth)acrylamide, N-(dimethylhydroxyethylammonium)
 15 propyl (meth)acrylamide etc., where the counterion may be chloride, bromide, acetate, propionate, laurate, palmitate, stearate etc., or the modified products with propane sultone of the aforementioned amine derivatives of (meth)acrylic acid or (meth)acrylamide. The
 20 monomers can also be N,N-dimethyldiallyl ammonium salt of an organic or inorganic counterion.

Ammonium group containing polymers can also be prepared by acidifying the amino group of the polymer with organic or inorganic acid to a pH where
 25 the pendant amino groups are substantially protonated. Totally substituted ammonium group containing polymers may be prepared by alkylating the above described amino polymers with alkylating groups, the method being commonly known in the art as the Menshutkin reaction.

30 The highly polar A monomers can also be sulphonic acid group containing monomers e.g. vinyl sulphonic acid, styrene sulphonic acid, 2-acrylamido-2-methyl propane sulphonic acid, allyloxybenzene sulphonic acid etc. These monomers may
 35 be used in the protonated acid form as monomers, with the corresponding polymers neutralized with an organic and inorganic base to give the salt form of the polymers.

The highly polar monomers can be other


- 15 -

alkenyl heterocycles such as vinyl pyridines, vinyl imidazoles, vinyl benzimidazoles, 2-ethenyl-4, 4-dimethyl-1, 3-oxazoline-5-one (vinyl azlactones), N-vinyl pyrrolidone (NVP), vinyl furans etc. These heterocyclic comonomers provide sites for hydrogen bonding with polar substrates and improve adhesion of the resultant polymers to such substrates.

The polymers for use in the compositions of the present invention are prepared by polymerizing the vinyl-silicone copolymers using a mercapto functional silicone chain transfer agent. The terms "mercapto functional silicone compounds", "mercapto functional silicone chain transfer agent", and "mercapto functional silicone macromolecular chain transfer agent" are used interchangeably throughout. The reaction comprises free radical polymerization of mercapto functional silicone with vinyl monomers.

Mercapto Functional Silicone Chain Transfer Agents

The formula of the mercapto functional silicone macromolecular chain transfer agent useful in the preparation of vinyl-siloxane copolymer is set forth below.



wherein all moieties are as defined above and wherein R_5 are monovalent moieties which can be the same or different and are selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, hydroxyl, fluoroalkyl, hydrogen, and -ZSH wherein Z is a divalent linking group. Useful divalent linking groups Z include but are not limited to the following: C_1 to C_{10} alkylene, alkarylene, arylene, and alkoxyalkylene.

- 16 -

Preferably, Z is selected from the group consisting of methylene and propylene.

When R_5 does not comprise a -ZSH group, R_5 is preferably selected from the group consisting of C_{1-3} alkyl or fluoroalkyl, and phenyl. Most preferably, R_5 comprises a methyl group.

R_6 are monovalent moieties which can be the same or different and are selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, hydroxyl, fluoroalkyl, hydrogen, and -ZSH, wherein Z is a divalent linking group as defined above.

R_6 does not comprise a -ZSH group, R_6 is preferably selected from the group consisting of C_{1-3} alkyl or fluoroalkyl, and phenyl. When R_6 does not comprise a -ZSH group, R_6 most preferably comprises a methyl group.

In the structure illustrated above, y is an integer of 5 or greater. Preferably, y is an integer ranging from about 10 to about 270 in order to provide the silicone segment with a molecular weight ranging from about 750 to about 20,000. Most preferably, y is an integer ranging from about 40 to about 270 in order to provide a silicone segment with a molecular weight ranging from about 3,000 to about 20,000 in order to provide a mercapto functional compound having a lower ratio of mercapto functional groups to mercapto functional silicone compounds. x and q are integers of 0 to 3, wherein at least one of the following is true:

q is an integer of at least one; x is an integer of at least one; R_5 comprises at least one -ZSH moiety; or R_6 comprises at least one -ZSH moiety.

The number of mercapto functional groups on the mercapto functional silicone compound can vary. The term "mercapto functional group", as used herein, refers to -ZSH, $-R_2SH$, and $-R_4SH$, wherein Z, R_2 , and R_4 are as previously defined. The ratio of the weight of mercapto functional groups to the total weight of the

- 17 -

mercapto functional silicone compound can range from about 0.5:99.5 to about 15:85. Preferably, the weight ratio of mercapto functional groups to mercapto functional silicone compound ranges from about 2:98 to about 10:90 in order to provide vinyl-siloxane copolymers with very low levels of free silicone without introducing too many mercapto functional groups. If the ratio of mercapto functional groups to mercapto functional silicone compound is too high, desired properties such as desirable sensational feeling in makeup cosmetics, and soft feel in hair care cosmetics will be lost. If the ratio of mercapto functional groups to mercapto functional silicone compound is too low, desired properties such as, style retention properties in hair care compositions may not be obtained.

The mercapto functional silicone compounds useful in the method of the present invention can be prepared by any known method including, for example, (1) cohydrolysis-condensation of a mixture consisting of an organoalkoxysilane having one or more mercapto-substituted hydrocarbon groups and an alkoxysilane possessing no mercapto group, (2) reaction of an organoalkoxysilane having one or more mercapto-substituted hydrocarbon groups with a cyclic organopolysiloxane or with a silanol terminated diorganopolysiloxane possessing no mercapto groups, (3) an equilibration reaction of a cyclic or linear chain organopolysiloxane having one or more mercapto substituted hydrocarbon groups with a cyclic or linear chain organopolysiloxane having no mercapto groups, (4) reaction of an organopolysiloxane having one or more nucleophilic groups such as an aminoalkyl with an electrophilic reagent such as 3-mercaptopropionic acid, in order to yield a mercapto-derivatized organopolysiloxane, and (5) reaction of an organopolysiloxane having one or more electrophilic

- 18 -

groups such as haloalkyl with a nucleophilic reagent such as an alkali metal sulfide to yield a mercapto-derivatized organopolysiloxane.

U.S. Pat. No. 4,238,393; U.S. Pat. No. 4,046,795; U.S. Pat. No. 4,783,490; U.S. Pat. No. 5,032,460 and Canadian Patent 1,233,290 describe the preparation of mercapto functional silicone compounds.


In order to form a graft vinyl-silicone copolymer, at least one mercapto functional group of the mercapto functional silicone compound must be bonded to a silicon atom within the silicone segment. Thus, at least one R_5 group or one R_6 group of the mercapto functional silicone compound must comprise -ZSH in order to form a vinyl-silicone graft copolymer, regardless of the existence of any mercapto functional group bonded to the terminal silicon atom.

Polymerizable Silanes



The polymerizable silanes are acryloxyalkyl-alkoxysilanes having a general formula of $D(G)SiR_1(Q)_{3-1}$ wherein symbol D represents the group $CH_2=C(R')-COO-$. The symbol R which may be the same or different, represents methyl, ethyl, n-propyl, vinyl or phenyl group. The symbol R' represents a hydrogen atom or a methyl group, the symbol Q, which may be the same or different, represent methoxy, ethoxy, n-propoxy or β -methoxyethoxy groups, and any two of the symbols Q taken together can represent a group of the formula:



The symbol G represents a linear or branched chain alkylene having 1 to 8 carbon atoms, and the symbol a represents a value of zero to two. Representative examples of silanes are:



- 19 -



20

These silanes may be prepared by reaction of intermediates of the formula $\text{Cl-G-SiR}_n(\text{Q})_{3-n}$ with organic acid of the formula $\text{CH}_2 = \text{C(R')} \text{COOH}$. The reaction is advantageously conducted in an organic aprotic solvent such as N-methylpyrrolidone-2, N,N-dimethylformamide, and in the presence of an HCl acceptor such as triethylamine. In place of the organic acids, their alkali metal salts may be used; in this case, it is unnecessary to utilize an HCl acceptor in the reaction mixture. The silanes are readily available on the silicone market. These silanes when desired can be used in 0.01% to 20% and preferably from 0.05% to 10% during polymerization.

35 Methods of Initiation

The homolytic decomposition of the initiator to form free radicals can be induced by heat energy (thermolysis), light energy (photolysis), or the addition of a suitable catalyst. "Initiator free"

- 20 -

polymerization may also be induced electronically or by exposure to ionizing radiation.

The decomposition rate of the initiator during thermolysis depends on the chemical nature of the initiator, the reaction temperature, and the solvent (if any) used.

The decomposition rate of the initiator during photolysis depends mainly on the chemical nature of the initiator and the intensity and wavelength of the radiation.

Light energy can be supplied to induce the homolytic decomposition of the initiator by means of visible or ultraviolet sources including low intensity fluorescent black light lamps, medium pressure mercury arc lamps, and germicidal mercury lamps.

The selection of a preferred light energy source will depend on the chosen photoinitiator.

The decomposition of the initiator can also be accomplished by using a suitable catalyst. Catalyst induced initiator decomposition involves an electron transfer mechanism resulting in a reduction-oxidation (redox) reaction. Initiators such as peroxides and hydroperoxides are more susceptible to this kind of decomposition.

Catalysts useful in inducing the homolytic decomposition of the initiator include but are not limited to the following: amines and metal ions used in combination with peroxide or hydroperoxide initiators, and bisulphite or mercapto compounds used in combination with persulphate initiators.

The preferred method of initiation comprises thermolysis which can be readily used in standard reactors. Thermolysis also provides ease of control of the reaction rate and exotherm.

Initiators

Useful initiators in the polymerization

- 21 -

method of the present invention are well known to practitioners skilled in the art and are detailed in chapters 20 & 21, *Macromolecules*, vol 2, 2nd Ed., H. G. Elias, Plenum Press, 1984, New York. Useful thermal

5 initiators for use in the method of the present invention include, but are not limited to the following: azo compounds such as 2,2'-azobis-(isobutyronitrile), dimethyl-2,2'-azo-bis-isobutyrate, azo-bis-(diphenyl methane), 4,4'-azo-bis-

10 (4-cyanopentanoic acid); peroxides such as benzoyl peroxide, cumyl peroxide, tert-butyl peroxide, cyclohexanone peroxide, glutaric acid peroxide, lauroyl peroxide, methyl ethyl ketone peroxide; hydrogen peroxide, hydroperoxides such as tert-butyl

15 hydroperoxide, and cumene hydroperoxide; peracid such as peracetic acid and perbenzoic acid, potassium persulfate; and peresters such as diisopropyl percarbonate.

Certain of these initiators (in particular

20 the peroxides, hydroperoxides, peracids, and peresters) can be induced to decompose by addition of a suitable catalyst rather than thermally. This redox method of initiation is described in Elias, Chapter 20.

Useful photochemical initiators include but

25 are not limited to benzoin ethers such as diethoxyacetophenone, oximino-ketones, acylphosphine oxides, diaryl ketones such as benzophenone, and 2-isopropyl thioxanthone, benzil and quinone derivatives, and 3-ketocumarines as described by S. P.

30 Pappas, *J. Rad. Cur.*, July 1987, P. 6.

Preferably, the initiator used comprise a thermally decomposed azo or peroxide compound for reasons of solubility and control of the reaction rate. Most preferably, the initiator used comprises 2,2'-

35 azobis(isobutyronitrile) for reasons of cost and appropriate decomposition temperature.

- 22 -

Solvents

The use of a solvent is optional in the present polymerization method. Preferably, a solvent is utilized for reasons of decreasing the viscosity during the reaction to allow for efficient stirring and heat transfer. The organic solvent used in the free radical polymerization can be any organic liquid which is inert to the reactants and which will not otherwise adversely affect the reaction.

Suitable solvents include but are not limited to esters such as ethyl acetate and butyl acetate; ketones such as methyl ethyl ketone, methyl isobutyl ketone, methyl propyl ketone, and acetone; alcohols such as methanol, ethanol, isopropanol, and butanol; and mixtures of two or more of the above mentioned solvents.

Other solvent systems are useful as well. Aliphatic and aromatic hydrocarbons can very well be used though some time they lead to the precipitation of the vinyl polymeric segment from solution, resulting in a non-aqueous dispersion polymerization. Such hydrocarbon solvents become more useful when admixed with other polar solvents providing a good control on molecular weight of the final polymer.

Low-viscosity silicone oil with linear, cyclic, or branched structure having a boiling point below 260°C, at normal pressure, and a viscosity below 100 cSt, such as polydimethylpolysiloxane with a low degree of polymerization, octamethylcyclotetrasiloxane(D₄), decamethylpentacyclotetrasiloxane(D₅), phenylpentamethyldisiloxane, hexamethyldisiloxane, phenethylpentamethyl disiloxane, and the like, can very well be used. Hexamethylcyclotrisiloxane(D₃) can be present in small amount in the above mixtures, but is generally not usable to solubilize the copolymers as it is solid at room temperature.

The solvent, if utilized in the free radical

- 23 -

polymerization, may be any substance which is liquid in a temperature range of about -10°C to about 50°C, does not interfere with the energy source or catalyst used to dissociate the initiator to form free radicals, is
5 inert to the reactants and product and will not otherwise adversely affect the reaction. The amount of solvent, if used, is generally about 30 to 95 percent by weight based on the total weight of the reactants and solvent. Preferably, the amount of solvent utilized
10 ranges from about 40 to about 65 percent by weight based upon the total weight of the reactants and solvent for reasons of yielding fast reaction times and high molecular weight of the polymer at appropriate product viscosities.

15 If the polymerization is conducted in the absence of a solvent, the free-radically polymerizable mixture of vinyl monomer, and mercapto functional silicone should remain homogeneous during the course of the reaction, allowing for the desired reaction between
20 the mercapto functional silicone, initiator, and monomers.

Method of Polymerization

The free radically polymerizable monomers,
25 the initiator, the mercapto functional silicone compound and any solvent employed are charged into an appropriate vessel. But, alternatively, if desired, these monomers can also be used in such a way that some of them in types and/or amounts are added to the
30 polymerization reaction separately. If photolysis is conducted to decompose the initiator, the reactants and any solvent employed are charged into an energy source-transparent vessel and therein subjected to the energy source. If the energy source is ultraviolet
35 light radiation, a suitable ultraviolet light-transparent vessel is utilized.

If thermolysis is used to decompose the

- 24 -

initiator, the reactants and any solvent employed are charged into a suitable glass or metal reactor, and therein subjected to the thermal energy source. If catalysis is used to decompose the initiator, a glass
5 or metal reactor can also be utilized.

The reaction is preferably conducted in a vessel with agitation to permit uniform exposure of the reactants to the energy source. While most of the reactions have been conducted by employing a batch
10 process, it is possible to utilize the same technology in a continuous polymerization operation.

Reaction times on the order of 1 to 40 hours have been found typical, depending upon the amount and type of solvent used, the amount and type of initiator
15 used, temperatures or photolytic energy supplied, and the nature of the free radically polymerizable monomers.

The block or graft copolymers when necessary or desirable can be blended with a compatible modifier
20 in order to optimize physical properties. The use of such modifiers is common in the art. For example, it may be desirable to include such materials as pigments, fillers, stabilizers, or various polymeric additives.

The vinyl-silicone copolymers can be
25 recovered by standard procedures such as evaporation of solvent, precipitation after polymerization into a suitable organic solvent such as methanol, hexane etc. Standard extraction techniques can also be used if desired. Polymer can also be taken into a different
30 solvent either by solvent exchange process, e.g., by adding a higher boiling solvent and then distilling out the low boiling solvent or by azeotropic distillation, a technique well known in the art.

Waterborne coatings can also be prepared by
35 following the method disclosed in U.S. Pat. No. 5,032,460 to Kantner et al.

Vinyl-silicone copolymers suitable for

- 25 -

waterborne applications are either those containing ionic functionalities in the vinyl polymeric block or segment or those containing acidic or basic functionalities which on neutralization yield ionic functionalities. Certain of these polymers can be modified to obtain a water dispersible formulation by a neutralization technique, specifically those copolymers containing acidic or basic functionality in the vinyl segment.

10 Copolymers containing acidic functionality are obtained by copolymerizing acidic monomers into the vinyl block or segment. Suitable acidic monomers include those containing carboxylic acid functionality such as acrylic acid, methacrylic acid, itaconic acid, 15 etc.; those containing sulfonic acid functionality such as 2-sulfoethyl methacrylate; and those containing phosphonic acid functionality.

Copolymers containing basic functionality are obtained by copolymerizing basic monomers into the 20 vinyl block or segment. Suitable basic monomers include those containing amine functionality such as vinyl pyridine, N,N-diethylaminoethyl methacrylate, N,N-dimethylamino-ethyl methacrylate, N,N-diethylaminoethyl acrylate, N,N-dimethylaminoethyl 25 acrylate, and N-t-butylaminoethyl methacrylate.

Preferred acidic monomers include acrylic acid and methacrylic acid. Preferred basic monomers include N,N-dimethylaminoethyl methacrylate, and N,N-dimethyl-aminoethyl acrylate.

30 In order to achieve water compatibility or dispensability, a certain minimum ionic content in the copolymer is required. The exact amount varies with the particular polymer formulation, the molecular weight of the polymerized silicone segment, and other 35 features of the individual copolymer. Generally a minimum of about 2% by weight of ionic content will yield a stable dispersion, considering the weight of

- 26 -

the ionic group to include only the simplest of constructions, e.g., the monomer from which the ionic group is derived plus the base or acid used to neutralize it, as the molecular weight of the ion.

- 5 Preferred copolymers incorporate above about 4% ionic content.

These vinyl-silicone copolymers, in addition to skin care products, such as cosmetics, can also be used in a variety of applications such as ink

10 receptive, thermoplastics, mold release agents, mildew preventives, moth resisting agents, corrosion resistant materials, softeners, permselective membranes, fabric protectors, textile treatment, additives to paints and varnishes such as wall paints, automotive paints and

15 the like, marine anti-fouling agents, and metal coatings etc. In accordance with the present invention, these copolymers can be utilized to formulate various other type of cleaning products which are not directly used on skin. Examples of such

20 products are cleaning products for shower area such as hard surface cleaner, laundry products, dish washing products, and the like to impart a smooth, silky, and water repellent properties on such surfaces.

25 Cosmetic Compositions Containing Vinyl-Silicone Copolymers

Low-viscosity silicone oil can be incorporated into the copolymer to provide a stable gel composition. There are no specific limitations as to

30 the type of a low-viscosity silicone oil for use. Any silicone oil having a viscosity below 100 cSt, preferably of 2-20 cSt, can suitably be used. The use of a large amount of a higher viscosity silicone oil may decrease the mutual solubility of the silicone oil

35 and vinyl-silicone copolymer. This results in an oily sensation and tends to impair the feeling upon use of the resulting product. Examples of low-viscosity

- 27 -

silicone oils include low-polymerization-degree polydimethylsiloxanes, polymethylphenylsiloxane, and the like. If necessary, two or more of low-viscosity silicone oils can be used in combination. Silicone oil
5 of the type mentioned above can be used as a low-viscosity silicone oil either independently or in combination. A desirable range to be incorporated is 30-94.8% by weight.

A gel composition of the present invention
10 usable in cosmetics, personal hygiene, and personal care products can be prepared by blending vinyl-silicone copolymer and a low-viscosity silicone oil and heating the mixture to dissolution; or by dissolving component into a volatile organic solvent,
15 and adding a low-viscosity silicone oil to the solution, followed by removal of the volatile organic solvent; or by carrying out the polymerization in low-viscosity silicone oils. The ratio of vinyl-silicone copolymer to low-viscosity silicone oil
20 varies depending on the type of copolymer. Normally, the ratio by weight of vinyl-silicone copolymer to low-viscosity silicone oil is 5:95 to 70:30, with a preferable range being 10:80 to 40:60. If the amount of the low-viscosity silicone oil is too large in
25 proportion to copolymer, the resulting gel composition becomes fluid so that a gel composition having acceptable solidity can not be obtained. If the amount of the copolymer is too large, on the other hand, a soft flexible solid gel composition cannot be obtained.

30 In the present invention, a solid gel composition having varied solidity, ranging from a comparatively hard gel to a comparatively soft gel, can be produced by changing the proportion of copolymer and a low-viscosity silicone oil, or the vinyl chain
35 length, silicone chain length and/or amount of silicone in the copolymer. If the proportion of the vinyl-silicone copolymer is increased or a larger

- 28 -

amount of methylmethacrylate is introduced into the vinyl chains of the copolymer, a solid gel giving suitable solidity to touch is obtained. On the other hand, a soft, flexible gel composition can be produced
5 by introducing a large amount of butylacrylate, or 2-ethylhexyacrylate into the vinyl chains of the copolymer.

The solid gel composition thus prepared gives a soft, stable, smooth, and fresh sensation upon use.
10 By using the solid gel composition as a component, very useful cosmetic compositions, in which the excellent characteristics of the solid gel are fully exhibited, can be produced. Such cosmetics include basic cosmetics for use with the face, hands, and feet such
15 as creams, emulsions, and the like; hair cosmetics such as hair treatment agents, and the like; makeup cosmetics such as foundations, rouges, face powders, lipsticks, eyeliners, eyeshadows, mascaras, and the like; protective cosmetics such as insect repellent
20 cream, sunscreen lotion/cream, and the like; and personal care/personal hygiene products such as toothpaste, deodorants, antiperspirant, and the like. The kind of cosmetics to which the gel composition of the present invention is applied are by no means
25 limited to those given here.

The amount of the solid gel to be incorporated into a cosmetic composition can be determined depending on the use to which the cosmetic composition is directed within a range of 1-100% by
30 weight. The use of the solid gel alone may achieve the purpose of the present invention.

The gel composition may comprise a small amount of partially crosslinked vinyl-silicone copolymer or partially crosslinked organopolysiloxane
35 polymeric compound. When incorporated in cosmetic compositions, these polymers provide a smooth and fresh feel upon use. A gel composition comprising 5-60% by

- 29 -

weight of a vinyl-silicone copolymer, 30-94.8% by weight of a low-viscosity silicone oil, and 0.2-40% by weight of a partially crosslinked organopolysiloxane is particularly useful for incorporating in a cosmetic composition. The amount of 5-60% by weight of vinyl-silicone copolymer is preferable, because the intended effect can not be produced if the amount is less than 5% by weight, and the cosmetic composition becomes too hard at an amount exceeding 60% by weight. If and when desired, partially crosslinked organopolysiloxane polymeric compound can be incorporated in the gel composition by simply blending the vinyl-silicone copolymer, the low-viscosity silicone oil, and partially crosslinked organopolysiloxane polymeric compound. An alternative method is to prepare a gel composition from the vinyl-silicone copolymer and the low viscosity silicone oil, and a gel composition from the partially crosslinked organopolysiloxane polymeric compound and the low-viscosity silicone oil, followed by blending the two gel compositions. This latter method can produce a gel composition having different characteristics from that produced by blending the three components at the same time. Specifically, such a gel composition can contain a greater amount of silicone oil in a more stable manner. This provides the resulting cosmetic composition with superior smoothness and freshness as well as even better stability over time. This gel composition can be incorporated in an amount of 2-100% by weight based on the total weight of the cosmetics and personal care composition.

Vinyl-silicone copolymers have excellent film-forming capability. Thus, the cosmetic and personal care compositions to which these copolymers are incorporated can produce a film exhibiting a superior water-resistance, oil-resistance, and other

- 30 -

characteristics required for cosmetic films. Taking a cosmetic composition for application to nails such as a nail enamel as an example, such a cosmetic composition can be prepared by dissolving the vinyl-silicone

5 copolymer into a low-boiling-point oil or a volatile solvent. The cosmetic composition thus prepared can produce a continuous film immediately upon application. The low-boiling-point oil used here includes volatile hydrocarbon oils having a boiling point below 260°C, at

10 normal pressure. There are no special limitations as to the types of hydrocarbons. Any types usually used for cosmetics can be used. Examples of a volatile solvent include ethyl acetate, butyl acetate, acetone, toluene, ethyl alcohol, i-propyl alcohol, n-propyl

15 alcohol, 1,2-propylene glycol, 1-methoxy-2-propanol, and the like. Another type of low boiling-point oil is a volatile, linear, cyclic, or branched silicone oil having a boiling point below 260°C, at normal pressure and a viscosity below 10 cSt, such as polydimethyl-

20 siloxane with a low degree of polymerization, octamethylcyclotetrasiloxane(D4), decamethylcyclopentasiloxane(D5), phenylpentamethyldisiloxane, hexamethyldisiloxane, phenethylpentamethyldisiloxane, and the like. The amount of vinyl-silicone copolymer

25 to be incorporated into the cosmetic composition is usually 0.03-70% by weight, and preferably 0.2 to 30%. If the amount of the copolymer is too small, the film produced by the cosmetic composition becomes so thin that the intended effect can not be exhibited. On the

30 other hand, too much inclusion of the copolymer results in a high viscosity product which is hard to apply and may give stiff feeling. Characteristics of films produced by conventional cosmetics are controlled by the addition of camphor, phthalic acid derivative, or

35 alkyd resin. In the cosmetic and personal care composition of the present invention, however, such characteristics can be controlled by adjusting the

- 31 -

acrylic chain composition and/or equivalent weight/molecular weight of silicone chain in the copolymer. For example, a hard film can be produced by introducing a large amount of monomers such as

5 methylmethacrylate, t-butyl(meth)acrylate, isobutylmethacrylate etc. into acrylic chains, while a soft film that is more soluble in a solvent can be produced by using a greater amount of butylacrylate, 2-ethyl hexylacrylate, or mercapto functional silicone;

10 or combination thereof.

A non-aqueous type protective or makeup cosmetic such as insect repellent cream, sunscreen cream, eyeliner, mascara, or the like can be produced by dissolving the vinyl-silicone copolymer into the

15 aforementioned volatile hydrocarbon oil or volatile silicone oil. The volatile component evaporates when this type of makeup cosmetic is applied to the object, thereby producing a continuous film. The amount of copolymer to be incorporated into such a makeup

20 cosmetic composition is usually 0.01-65% by weight, and preferably 0.5-35% by weight. If the amount of copolymer is too small, a continuous film can not be produced, and thus the intended effect can not be adequately exhibited, although this will depend on

25 other components such as waxes or pigments. If the amount of the copolymer is too large, the viscosity becomes so high that the usability of the product is impaired.

Protective and makeup cosmetic compositions

30 can also be prepared by using vinyl-silicone copolymer of the present invention, low-boiling-point oil, a cosmetic material, and a polyacrylic emulsion of the type increasing its viscosity under alkaline conditions. Such a cosmetic composition produces a

35 uniform film which possesses improved water-resistance and produces a thick-film sensation after the application.

- 32 -

Personal hygiene and personal care products such as deodorant, antiperspirants, tooth paste and the like can also be prepared by using vinyl-silicone copolymer of the present invention, low-boiling-point oil, and other necessary ingredients. Such a cosmetic composition provides improved water-resistance and poor adherence of bacteria to such surfaces thereby providing a fresh feeling. Fewer or no stains are observed on teeth in the case of tooth paste.

10 The aforementioned volatile hydrocarbons or silicone oils having a boiling point below 260°C at normal pressure can be used as the low-boiling-point oil. They can be used either independently or as a mixture. Their amount in the makeup cosmetic
15 composition is 2-70% by weight, and preferably 5-40% by weight. The low boiling-point oil functions as a solvent of the copolymer. It also plays an important role in spreading and promoting the life of the cosmetic film.

20 There are no specific limitations as to the cosmetic powder material used in the makeup cosmetic composition. It may be a body pigment, inorganic white pigment, inorganic colored pigment, organic pigment, organic powder, pearling agent, or the like. Specific
25 examples are talc, mica, magnesium carbonate, calcium carbonate, magnesium silicate, aluminum magnesium silicate, silica, titanium dioxide, zinc oxide, red iron oxide, yellow iron oxide, black iron oxide, ultramarine blue, tar pigment, nylon powder,
30 polyethylene powder, methacrylate powder, polystyrene powder, polytetrafluoroethylene powder, silk powder, crystalline cellulose, starch, titanated mica, iron oxide titanated mica, bismuth oxychloride, and the like. These cosmetic powder may be used after a
35 surface-treatment with an oily agent such as silicone or the like. They can be used independently, or two or more of them can be used in combination.

- 33 -

The amount of the cosmetic powder material used for the makeup cosmetic composition can be determined depending on the intended use or purpose without limitation. Usually, an amount of 5-40% by weight is preferable.

Polyacrylic emulsions of the type increasing viscosity of the cosmetic composition under alkaline conditions are homopolymers of acrylic acid, or methacrylic acid, their copolymers, and partially cross-linked acrylic acid polymers. They increase the viscosity of cosmetic compositions when neutralized with an alkali. These cosmetic component emulsions may be used independently, or two or more of them can be used in combination. The amount of the composition to be incorporated in the cosmetic composition of the present invention is 1-10 % by weight. Within this range, the emulsion component can homogeneously disperse the solution of the vinyl-silicone graft copolymer in the low boiling-point oil in an aqueous phase. If the amount is less than 1% by weight, the dispersion can be achieved only insufficiently, resulting a product having an inadequate viscosity. On the other hand, if the amount is greater than 10% by weight, the product becomes too viscous to be conveniently applied. Any alkaline substance commonly used for cosmetics can be used to neutralize the polyacrylic emulsion and to raise its viscosity. Suitable examples are inorganic alkalies such as sodium hydroxide and potassium hydroxide, basic amino acids such as L-arginine, amines such as triethanolamine, and ammonia, and the like. The amount of alkali used in the cosmetic composition is determined taking into account the type of the alkali and the type of polyacrylic emulsion which are used for preparing the cosmetic composition. Usually, a preferable amount is 0.03-2.5% by weight. The alkali is added, for example, by dissolving it in water, or by directly mixing it

- 34 -

with the polyacrylic emulsions. The method of the addition of an alkali, however is not limited by these.

The cosmetic composition may be in oil-in-water (o/w) type emulsion or water-in-oil (w/o) type
5 emulsion. An o/w and w/o type emulsion cosmetic compositions can be prepared by using the copolymer and the low boiling-point oils at a specific proportions. These emulsion cosmetic compositions exhibit a smooth spreadability on the skin without imparting an oily
10 sensation, and yet, upon application produce a film having excellent water-repellency. They also possess good stability over time. One or more type of copolymers can be used and incorporated into these emulsions.

15 The non-aqueous type makeup cosmetic composition of the present invention can be prepared by blending the above components according to a conventional method and can be prepared into various forms, including a cream, and a liquid in which the
20 cosmetic powder materials are homogeneously dispersed or precipitated. The cosmetic composition is applied to foundation, eyeshadows, rouges, face powders, and the like.

The oil-in-water type emulsion cosmetic
25 composition comprises 1-50% by weight of an oily component mixture which comprises 1-40% by weight of the copolymer and 2-60% by weight of the low boiling-point oil, wherein the amount of vinyl-silicone copolymer plus low boiling-point oil in the total oily
30 component mixture is 50-100% by weight. The vinyl-silicone copolymer plays an important role in the high water-repellency possessed by the o/w type emulsion cosmetic composition. The amount of this copolymer in the oily component mixture is in the range
35 of 1-40% by weight. An amount of less than 1% by weight does not produce a sufficient water-repelling characteristics in the emulsion cosmetic composition.

- 35 -

An amount exceeding 40% by weight of the copolymer in the mixture raises the viscosity of the resulting emulsion cosmetic composition. This affects the readiness in the application of the emulsion cosmetic composition to the skin and imparts an oily feeling to the skin. The aforementioned low boiling-point oils can be used for the oily component mixture for producing an o/w type emulsion cosmetic composition. They may be used independently or two or more of them can be used in combination. The low boiling-point oil dissolves the copolymer thereby producing a homogeneous oil phase. After application of the emulsion cosmetic composition, it evaporates leaving a good cosmetic film on the skin. The amount of the low boiling-point oil in the oil component mixture is suitably determined taking into account the amount of copolymer and other factors. Usually, the preferable amount is 2-60% by weight. If the amount is smaller than 2% by weight, the resulting cosmetic composition in which a comparatively large amount of the copolymer is incorporated exhibits only poor spreadability and imparts an oily feeling upon use. If greater than 60% by weight, a longer time is required for the emulsion cosmetic composition to be fixed and the cosmetic composition tends to leave a thin film after makeup. The total amount of the vinyl-silicone copolymer and the low-boiling-point oil in the oil component mixture is 5-100% by weight and preferably 10-60% by weight. If the amount is smaller than 10% by weight, the water repellency and the excellent feeling upon use of the resulting emulsion cosmetic composition are lost.

Oil components other than the vinyl-silicone copolymer, and the low boiling-point oil which can be used for the oil component mixture for producing the emulsion cosmetic composition of the present invention may be liquid, semisolid, or solid oils. Specific examples include liquid, paste, or solid hydrocarbons

- 36 -

such as liquid paraffin, squalane, and the like; waxes, higher fatty acids, higher alcohols, esters, glycerides, low and high molecular weight silicone oils, and the like. These oil components may be used
5 independently or two or more of them can be used in combination. They form a homogeneous oil phase together with the copolymer and low boiling-point oil. They also function as a plasticizer in the formation of a resin by the copolymer when the low boiling-point oil
10 evaporates. The oil component mixture containing a low-viscosity silicone oil is particularly preferable. The stability of the cosmetic composition and the feeling upon use can be remarkably promoted by the use of such a component mixture.

15 The oil component mixture comprising the above components is used in the o/w type emulsion cosmetic composition of the present invention in an amount of 5-40% by weight. If the amount is smaller than 5% by weight, a sufficient water repelling effect
20 can not be obtained. On the other hand, if the amount is greater than 40% by weight, the stability of the emulsion cosmetic composition tends to be impaired.

The oil-in-water type emulsion cosmetic composition can be prepared by emulsifying the oil
25 phase and the water phase according to a conventional method. It can be made into a cream, lotion or the like.

A makeup cosmetic composition comprising the vinyl-silicone graft copolymer, a low-viscosity
30 silicone oil and/or a low boiling-point oil, and a cosmetic powder material is another embodiment of the present invention. This makeup cosmetic composition has excellent water-repellency, oil-resistance, and water-resistance. It gives a good
35 feeling upon use, and its makeup effect lasts for a long period.

Makeup cosmetic compositions can easily be

- 37 -

prepared by utilizing the components already described above. Among this type of makeup cosmetic composition, a non-aqueous type makeup cosmetic composition comprising 0.03-40% by weight of the vinyl-silicone graft copolymer, 1-60% by weight of the low-viscosity silicone oil, 5-80% by weight of a volatile hydrocarbon, and 5-50% by weight of a cosmetic powder material is preferable composition. It has an excellent stability, water or sweat resistance, gives a good feeling upon use, and yet possesses improved oil or sebum resistance and friction resistance.

The vinyl-silicone graft copolymer is incorporated into the cosmetic composition in an amount of 0.03-40% by weight. If less than 0.03% by weight, the intended effect can not be obtained. If greater than 40% by weight, the cosmetic film produced gives a thick feeling.

The aforementioned low-viscosity silicone oil can be used in an amount of 1-60% by weight. If the amount of low boiling point silicone oil is less than 1% by weight, the result is a film with insufficient softness. On the other hand, with the amount exceeding 60% by weight, a long period of time is required for the makeup to "fix" after application. The resulting cosmetic film from a composition containing too much silicone oil is so thin that it gives an unsatisfactory feeling to the user.

The volatile hydrocarbons of the type previously mentioned when used in the cosmetic composition maintain the vinyl-silicone copolymer in a well-dissolved condition. After the cosmetic composition is applied to the skin, the solvent evaporates and a good cosmetic film is formed which lasts over a long period of time. It is desirable that the volatile hydrocarbon be incorporated in an amount of 5-80% by weight. If the amount is smaller than 5% by weight, the cosmetic composition produced has a

- 38 -

higher viscosity and does not spread well over the skin when applied. This leads to difficulty in forming a homogeneous film.

It is desirable that the cosmetic powder
5 material be added in an amount of 5-50% by weight of the total amount of the cosmetic composition. The specific amount depends on the intended use and intended application of the cosmetic composition.

As still another embodiment, the present
10 invention provides a water-in-oil type emulsion cosmetic composition comprising 0.3-30% by weight of a vinyl-silicone graft copolymer, 15-75% by weight of a low-viscosity silicone oil and/or a low-boiling-point oil, 0.1 - 10% by weight of a surface active agent, and
15 5-70% by weight of water. In this composition the total amount of vinyl-silicone copolymer plus low-viscosity silicone oil and/or low-boiling-point oil is 15-60% by weight. This w/o type emulsion cosmetic composition has good stability over time, produces a
20 film exhibiting a superior water-repellency, and gives an excellent feeling upon use. One or more types of the vinyl-silicone copolymers can be used and incorporated into the w/o type emulsion cosmetic composition in an amount of 0.3-30% by weight. An
25 amount smaller than 0.3% by weight does not give the sufficient intended effect. If the amount of the copolymer exceeds 30% by weight, the resulting cosmetic composition gives a heavy feeling to the skin when applied. In addition, an oily feeling impairs the use
30 value of the product.

The above mentioned low-viscosity silicone oil and low-boiling-point oil can be used in this w/o type emulsion cosmetic composition. The total amount of the low-viscosity silicone oil and low-boiling-point
35 oil is 15-60% by weight of the cosmetic composition. If the amount is less than 15% by weight, and especially the amount of the low-viscosity silicone oil


- 39 -

is too small, a smooth, water-repellent characteristic can not be exhibited effectively.

Besides the above defined components, synthetic or natural cosmetic oils conventionally used for cosmetics can be incorporated to the extent that the homogeneity of the oil phase is not adversely effected.

The vinyl-silicone copolymer and the low-viscosity silicone oil and/or the low-boiling-point oil are incorporated into the w/o type emulsion cosmetic composition in an amount of 5-60% by weight in total.

Oxyalkylene-modified organosiloxane type surface active agents which can emulsify water into the oily components of the cosmetic composition can be used as additional components without any special restriction. Oxyalkylene-modified organosiloxanes include polyether-modified silicones, and alkyl-polyether-modified silicones. Organosiloxanes shown below are presented as examples and are not limited by any means.



wherein G represents CH_3 , or $(\text{CH}_2)_p\text{O}(\text{C}_2\text{H}_4\text{O})_m(\text{C}_3\text{H}_6\text{O})_n\text{R}_a$, or $(\text{OC}_2\text{H}_4)_m(\text{OC}_3\text{H}_6)_n\text{OR}_b$ wherein p is 1-5, m is 1-50 and n is 0-30; R_a , and R_b represents a hydrogen atom or an alkyl group having 1-5 carbon atoms; X represents $(\text{CH}_2)_p\text{O}(\text{C}_2\text{H}_4\text{O})_m(\text{C}_3\text{H}_6\text{O})_n\text{R}_a$, or $(\text{OC}_2\text{H}_4)_m(\text{OC}_3\text{H}_6)_n\text{OR}_b$ wherein p, m, and n have the same meaning as defined above; a is 1-300, and preferably 1-30; and b is 1-350, and preferably 1-50. Each G and X can be same or different in a molecule. Moieties represented by repeating units a and b may also be present in a random fashion.

- 40 -

Organosiloxane surfactants that are liquid or paste at normal temperature and are water-insoluble are preferable. Specific examples are Silwet® L-722, and L-7500 surfactants (trade mark, Union Carbide Corporation), Silicone KF-945 surfactant (trade mark, Shin-Etsu Chemical Co., Ltd.), Silicone SH-3772C surfactant (trade mark, Toray Silicone Co., Ltd.), and the like. Since such an oxyalkylene-modified organopolysiloxane has a polysiloxane as the main chain, its mutual solubility with the vinyl-silicone graft copolymer, low-viscosity silicone oil, and low-boiling-point oil is excellent. This contributes to the formation of a stable emulsion.

An amount of 0.1-10% by weight, preferably of 0.5-5% by weight, of the surface active agent is incorporated into the w/o type emulsion cosmetic composition. If the amount is less than 0.1% by weight, a sufficient emulsification effect can not be exhibited. An amount exceeding 10% by weight tends to make the resulting product feel heavy and sticky.

Water is incorporated in an amount of 5 -69.9% by weight as one of the components.

In the preparation of the w/o type emulsion cosmetic composition, the vinyl-silicone graft copolymer, low-viscosity silicone oil, and/or low-boiling-point oil are dissolved in advance. Otherwise, a process conventionally used for the production of a w/o type emulsion cosmetic can be used for the preparation of the composition.

30

Hair Care Compositions

The vinyl-silicone copolymers as described herein are used in hair care products in an amount of 0.01 to 30% by weight, and preferably 0.1 to 10% by weight in well-known compositions such as shampoos, rinses, hair treatment products, hair setting products, cold permanent wave lotions or the like. The hair care

- 41 -

products into which the copolymer is incorporated may be of any form, such as liquid, cream, emulsion, gel or the like. It may also be used in combination with well-known conventional naturally occurring polymers, 5 modified products of naturally occurring polymers, or synthetic polymers.

Hair care products in which the copolymer in accordance with the present invention is used include hair conditioning compositions such as shampoos, 10 rinses, hair grooming products such as hair treatment lotions, cold permanent wave lotions and the like for providing hair with softness, gloss, smooth combing, recovery from damage, manageability, and the like and those for providing hair setting compositions for 15 setting hair in desired hair style such as aerosol hair sprays, pump hair sprays, foaming type hair sprays, hair mists, hair setting lotions, hair styling gels, hair liquids, hair creams, hair oils and the like.

The compositions of the invention also 20 comprise a carrier, or a mixture of such carriers, which are suitable for application to hair. The carriers are present at from about 0.5% to about 99.5%, preferably from about 5.0% to about 99.5%, and most preferably from about 10% to 90.0%, of the composition. 25 As used herein, the phrase "suitable for application to hair" means that the carrier does not damage or negatively affect the aesthetics of hair or cause irritation to skin. Choice of appropriate solvent will also depend on the particular copolymer to be used, and 30 whether the product formulated is meant to be left on hair (e.g., hair sprays, mousse, tonic) or rinsed off (e.g., shampoo, conditioner) after use.

The carrier used herein include solvents, as well as other carrier or vehicle components 35 conventionally used in hair care compositions. The solvent selected must be able to dissolve or disperse the particular silicone copolymer being used. The

- 42 -

nature and proportion of monomer in the copolymer largely determines the copolymer's polarity and solubility characteristics. The silicone copolymers can be designed, by appropriate selection of monomers, for formulation with a wide range of solvents. Suitable solvents for use in the present invention include, but are not limited to, water: lower alcohols such as ethanol or isopropanol; hydroalcoholic mixtures; hydrocarbons such as isobutane, hexane, decane or acetone; halogenated hydrocarbons such as FreonTM fluorocarbons; hydrocarbon esters such as ethyl acetate and dibutyl phthalate; volatile silicone derivatives, especially siloxanes, such as phenyl pentamethyl disiloxane, methoxypropyl heptamethyl cyclotetrasiloxane, chloropropyl pentamethyl disiloxane, hydroxypropyl pentamethyl disiloxane, octamethyl-cyclotetrasiloxane, and decamethyl cyclopentasiloxane; and mixtures thereof. The solvents used in such mixtures may be miscible or immiscible with each other.

The copolymers in accordance with the present invention are used in these hair care products as a partial or total substitute for or in combination with anionic, nonionic, cationic, and amphoteric polymers, and polysiloxane polymers conventionally used in these hair care products.

The hair care compositions in accordance with the present invention may be formulated in a wide variety of product types, including mousses, gels, lotions, tonics, sprays, shampoos, and conditioners. The additional components required to formulate such products vary with product type and can be routinely chosen by one skilled in the hair care product art.

The hair care compositions of the present invention are used in conventional ways to provide the hair conditioning/styling/hold benefits of the present invention. The method of use depends upon the type of

- 43 -

composition employed but generally involves application of an effective amount of the product to the hair, which may then be rinsed from the hair (as in the case of shampoos and some conditioning products), or allowed
5 to remain on the hair (as in the case of spray, mousse, gel, and tonic products). By effective amounts is meant an amount sufficient to provide the hair conditioning/ styling/hold benefits desired considering the length and texture of the hair, and the type of the
10 product used.

The cosmetic composition provided by the present invention can be applied to a wide variety of uses such as for basic cosmetics, makeup cosmetics, hair cosmetics, and the like. Besides the above
15 components various components conventionally used for cosmetics can be optionally incorporated into the cosmetic composition of the present invention to the extent that such incorporation does not impair the intended effects of the cosmetic composition. Such
20 optional components include alkali metal soaps, polyhydric alcohols, high molecular weight compounds, preservatives, alkaline agents, UV absorbers, anti-oxidants, tar-derived coloring agents, skin-improvers, humectants, perfumes, and the like.

25 The present invention is explained more specifically with reference to the following preparation examples and formulation examples without limit thereto. The parts and percentages in the preparation examples are represented by weight. The
30 parts and percentages in the formulation examples are represented by weight on the basis of effective components.

Examples

35 Examples 1-8 were prepared by a general method as described below.

- 44 -

A 250 ml three-necked flask was fitted with a magnetic stirrer, a condenser, a thermometer, a stopper, and a nitrogen inlet. The reaction apparatus was flushed with nitrogen. All the desired monomers, solvent and initiator were charged into the flask, and nitrogen was bubbled through the reaction mixture for 15 minutes. Polymerization was carried out by heating this reaction mixture at desired temperature for desired hours under positive pressure of nitrogen. Removal of solvent gave a solid polymer.

The mercapto functional silicone compound used in Example 1-8 are pendant functional, mercaptopolydi-organosiloxane of 100-200 centistokes viscosity with 5-10 mole% of 3-mercaptopropylmethylsiloxane unit and were obtained from Huls America, Inc (catalog # 850).

Example 1

Preparation of Copolymer using Mercapto Functional Silicone (PS 850), Acrylic Acid(AA), and n-Butyl Methacrylate(NBM)

To a mixture of 30 parts of PS850, 10 parts of AA, and 60 parts of NBM in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

Example 2

Preparation of Copolymer using Mercapto Functional Silicone (PS 850), Acrylic Acid(AA), and t-Butyl Acrylate (TBA)

To a mixture of 20 parts of PS850, 20 parts of AA, and 60 parts of TBA in 150 parts of methyl ethyl

- 45 -

ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

Example 3

Preparation of Copolymer using Mercapto Functional Silicone (PS 850), Ethylhexyl methacrylate (EHM), and i-Butyl Methacrylate (IBM)

To a mixture of 30 parts of PS850, 30 parts of EHM, and 40 parts of IBM in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

20

Example 4

Preparation of Copolymer using Mercapto Functional Silicone (PS 850), N-vinyl pyrrolidone (NVP), and i-Butyl Methacrylate (IBM)

25

To a mixture of 30 parts of PS850, 20 parts of NVP, and 50 parts of IBM in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

30

Example 5

Preparation of Copolymer using Mercapto Functional Silicone (PS 850), N,N-Dimethylacrylamide (DMA), and i-Butyl Methacrylate (IBM)

35

- 46 -

To a mixture of 25 parts of PS850, 10 parts of DMA, and 65 parts of IBM in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution
5 was purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

Example 6

10 Preparation of Copolymer using Mercapto Functional Silicone (PS 850), N,N-(Dimethylamino)ethyl Methacrylate (DMAEMA), and i-Butyl Methacrylate (IBM)

To a mixture of 20 parts of PS850, 10 parts
15 of DMAEMA, and 70 parts of IBM in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by
20 evaporation of solvent.

Example 7

Preparation of Copolymer using Mercapto Functional
Silicone (PS 850), and i-Butyl Methacrylate (IBM)
25

To a mixture of 30 parts of PS850, and 70 parts of IBM in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was
30 purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

Example 8

35 Preparation of Copolymer using Mercapto Functional Silicone (PS 850), and t-Butyl Acrylate (TBA)

- 47 -

To a mixture of 20 parts of PS850, and 80 parts of TBA in 150 parts of methyl ethyl ketone (MEK) was added 0.25 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was
5 purged with nitrogen and reaction was carried out at 60°C for 18 hours. Polymer was recovered by evaporation of solvent.

Examples 9-15 were prepared by the same
10 general procedure as described below.

A 16 oz narrow-mouth glass bottle was charged with the monomers, solvent, and initiator. The reaction solution was deoxygenated by bubbling the
15 nitrogen gas for 5-10 minutes. The bottle was then sealed with a foiled lined cap. The polymerizations were carried out in an Atlas Launder-O-Meter™ for 24 hrs.

The mercapto functional silicone compound
20 used in Example 9-15 are pendant functional, mercaptopoly-diorganosiloxane of 100-200 centistokes viscosity with 5-10 mole% of 3-mercaptopropylmethylsiloxane unit and were obtained from Shin-Etsu, Inc (catalog # KF2001).

25

Example 9

Preparation of Copolymer using Mercapto Functional Silicone (KF2001), and Methyl Methacrylate (MMA)

30 To a mixture of 10 parts of KF2001, and 90 parts of MMA in 100 parts of ethyl acetate (EtOAc) was added 0.1 parts (of monomers) of 2,2'-azobisisobutyronitrile (AIBN). This solution was purged with nitrogen and reaction was carried out at 60°C for 24
35 hours. Polymer was recovered by evaporation of solvent.

- 48 -

Example 10

Preparation of Copolymer using Mercapto Functional
Silicone (KF2001), and Ethyl Methacrylate (EMA)

5 To a mixture of 10 parts of KF2001, and 90
parts of EMA in 100 parts of ethyl acetate (EtOAc) was
added 0.1 parts (of monomers) of 2,2'-azobisiso-
butyronitrile (AIBN). This solution was purged with
nitrogen and reaction was carried out at 60°C for 24
10 hours. Polymer was recovered by evaporation of
solvent.

Example 11

Preparation of Copolymer using Mercapto Functional
15 Silicone (KF2001), and t-Butyl Acrylate (TBA)

 To a mixture of 10 parts of KF2001, and 90
parts of TBA in 100 parts of ethyl acetate (EtOAc) was
added 0.1 parts (of monomers) of 2,2'-azobisiso-
20 butyronitrile (AIBN). This solution was purged with
nitrogen and reaction was carried out at 60°C for 24
hours. Polymer was recovered by evaporation of
solvent.

Example 12

25 Preparation of Copolymer using Mercapto Functional
Silicone (KF2001), and i-Butyl Methacrylate (IBM)

 To a mixture of 10 parts of KF2001, and 90
30 parts of IBM in 100 parts of ethyl acetate (EtOAc) was
added 0.1 parts (of monomers) of 2,2'-azobisiso-
butyronitrile (AIBN). This solution was purged with
nitrogen and reaction was carried out at 60°C for 24
hours. Polymer was recovered by evaporation of
35 solvent.

Example 13

- 49 -

Preparation of Copolymer using Mercapto Functional
Silicone (KF2001), and n-Butyl Methacrylate (NBM)

To a mixture of 10 parts of KF2001, and 90
5 parts of NBM in 100 parts of ethyl acetate (EtOAc) was
added 0.1 parts (of monomers) of 2,2'-azobisiso-
butyronitrile (AIBN). This solution was purged with
nitrogen and reaction was carried out at 60°C for 24
hours. Polymer was recovered by evaporation of
10 solvent.

Example 14

Preparation of Copolymer using Mercapto Functional
Silicone (KF2001), i-Butyl Methacrylate (IBM), and
15 Acrylic Acid(AA)

To a mixture of 10 parts of KF2001, 10 parts
of AA, and 80 parts of IBM in 100 parts of ethyl
acetate (EtOAc) was added 0.1 parts (of monomers) of
20 2,2'-azobisisobutyronitrile (AIBN). This solution was
purged with nitrogen and reaction was carried out at
60°C for 24 hours. Polymer was recovered by
evaporation of solvent.

25

Example 15

Preparation of Copolymer using Mercapto Functional
Silicone (KF2001), i-Butyl Methacrylate (IBM), and
N,N-Dimethyl Acrylamide (DMA)

30

To a mixture of 10 parts of KF2001, 10 parts
of DMA, and 80 parts of IBM in 100 parts of ethyl
acetate (EtOAc) was added 0.1 parts (of monomers) of
2,2'-azobisisobutyronitrile (AIBN). This solution was
purged with nitrogen and reaction was carried out at
35 60°C for 24 hours. Polymer was recovered by
evaporation of solvent.

- 50 -

Following polymer formulations are prepared for their use in hair care compositions.

Formulation #1

5 5 Gram of copolymer prepared in Example 14
was dissolved in 50 ml of 200 proof ethyl alcohol.
After the polymer is dissolved, 1.25 g (equimolar
amount to acid) of 2-amino-2-methyl-1-propanol (AMP)
was added to it. The formulation thus obtained is
10 referred as F-1.

Formulation #2

6.4 Gram of copolymer prepared in Example 2
was dissolved in 50 ml of 200 proof ethyl alcohol.
15 After the polymer is dissolved, 1.61 g (equimolar
amount to acid) of AMP was added to it. The
formulation thus obtained is referred as F-2.

Formulation #3

20 20 Gram of the copolymer prepared in Example
8 was taken in 100 ml of isopropanol and 80 g of
octamethylcyclotetrasiloxane(D₄). Isopropanol is
removed from the mixture on rotary evaporator providing
a gel composition which is a uniform jelly. This
25 composition is usable in cosmetic formulations. The
formulation thus obtained is referred as F-3.

Formulation #4

20 Gram of the copolymer prepared in Example
30 3 was taken in 100 ml of isopropanol and 80 g of
octamethylcyclotetrasiloxane(D₄). Isopropanol is
removed from the mixture on rotary evaporator providing
a gel composition which is a uniform jelly. This
composition is usable in cosmetic formulations. The
35 formulation thus obtained is referred as F-4.

Formulation #5

- 51 -

20 Gram of the copolymer prepared in Example 7 was taken in 100 ml of isopropanol and 100 g of octamethylcyclotetrasiloxane(D₄). Isopropanol is removed from the mixture on rotary evaporator providing a gel composition which is a uniform solid. This composition is usable in cosmetic formulations. The formulation thus obtained is referred as F-5.

Example 16

10 A face cream composition representative of the present invention is prepared using the following formulation.

	Mineral Oil	15.00
	Cetyl Alcohol	2.00
15	Lanolin	2.00
	Arlacell 165 Emulsifier ¹	10.00
	Tween 60 Surfactant ¹	1.00
	Glycerine	6.00
	Octamethylcyclotetrasiloxane	10.00
20	Polymer of Example 3	2.00
	Water	52.00

		100.00

¹Available from ICI Americas

25

Example 17

A nail polish composition representative of the present invention is prepared using the following formulation.

30	D4	21.50
	Propylene Glycol	2.00
	Ethoxylan 50 ¹	1.00
	SD-Alcohol 40 ²	55.00
	Polymer of Example 4	20.00
35	D&C Red #22	0.50

		100.00

¹Available from Emery PCPG

²SD Alcohol 40 is ethyl alcohol denatured with brucine, 40 brucine sulfate, or quassin, and t-butyl alcohol.

- 52 -

Example 18

A lip gloss composition representative of the present invention is prepared using the following formulation.

5	Beeswax	25.00
	Drakeol 7 Mineral oil ¹	20.00
	Isopropyl Myristate	10.00
	Penreco Snow Petrolatum	20.00
	F-5	25.00
10		-----
		100.00

¹Available from Penreco

Example 19

15 A stick eyeshadow composition of the present invention is prepared using the following formulation.

	F-5	85.00
	Phenethylpentamethyldisiloxane	5.00
	Colored Pigments	4.50
20	Titanated Mica	3.5
	Mica	2.00

		100.00

Example 20

25 After-shave conditioning lotion representative of the present invention is prepared by using the following formulation.

	Ethanol(anhydrous)	91.00
30	Water	5.00
	F-2	2.00
	Fragrance	qs

Example 21

35 The shampoo composition, representative of the present invention was prepared using the following formulation.

	Sodium Laureth-7-sulphate	16%
	Lauroyl Diethanolamide	2.0%
	F-1	0.5%
40	DI Water	balance

		100%

- 53 -

When the composition was used for shampooing, hair after washing combed smoothly, and the hair after drying had an excellent gloss and brilliance and a smooth feeling.

5

Example 22

The shampoo composition, representative of the present invention was prepared using the following formulation.

10	Sodium Laureth-7-sulphate	16%
	Lauroyl Diethanolamide	2.0%
	F-2	0.5%
	DI Water	balance

		100%

15

When the composition was used for shampoos, excellent effects as in Example 16 were obtained.

Example 23

20

The rinse composition, representative of the present invention was prepared using the following formulation.

	Variquat 638	2.0%
	Lauroyl Diethanolamide	2.0%
25	F-2	0.5%
	DI Water	balance

		100%

Variquat 638 is a quaternary ammonium compound and is commercially available from Sherex Chemical Company, Inc.

When the composition was used for a rinse, hair after rinsing was combed smoothly, and the hair after drying had an excellent gloss and brilliance, and a smooth feeling so that the hair was combed smoothly.

35

Example 24

The rinse composition representative of the present invention was prepared by using the following

- 54 -

formulation.

	Variquat 638	2.0%
	Lauroyl Diethanolamide	2.0%
	Silicone Oil (10,000 mol.wt.)	0.5%
5	F-2	0.5%
	DI Water	balance

		100%

Variquat 638 is a quaternary ammonium compound and is
10 commercially available from Sherex Chemical Company,
Inc.

When the composition was used for hair rinse,
excellent effects as in Example 18 were obtained.

15

Example 25

The rinse composition representative of the
present invention was prepared by using the following
formulation.

20	Variquat 638	2.0%
	Lauroyl Diethanolamide	2.0%
	F-1	0.5%
	DI Water	balance

25		100%

Variquat 638 is a quaternary ammonium compound and is
commercially available from Sherex Chemical Company,
Inc.

When the composition was used for hair rinse,
30 excellent effects as in Example 18 were obtained.

Examples 26-30

The hair spray compositions representative of
the present invention were prepared as follows.

35 Copolymers of Example #2, Example #13,
Example #14, and Example #15 were dissolved in ethyl
alcohol to give 5% solution. Formulations were tested
by spraying the polymer solution on to hair swatches
with a pump. When these formulations were used by
40 spraying them onto hair, they gave very good set

- 55 -

maintaining the hold capability as well as a smooth feeling.

Example 31

A hair oil composition representative of the present invention was prepared using the following formulation.

	D4	40.00
	F-2	5.00
	Anhydrous Ethanol	balance
10		-----
		100.00

Example 32

An anti-perspirant composition representative of the present invention is prepared using the following formulation.

	¹ Bentonite Gel Rheological additive	8.0
	² Arlamol E Emollient	3.0
	F-4	3.0
20	² Arlacel 80 Emulsifier	0.50
	³ Macrospherical 95 Antiperspirant	6.00
	⁴ Propellant A-46	balance

		100.00

¹commercially available from NL Industries, Inc.

²commercially available from ICI Americas, Inc.

³commercially available from Reheis Chemical Co.,

⁴hydrocarbon propellant available from Phillips Chemical Co.

30

Example 33


A toothpaste composition representative of the present invention is prepared using the following formulation.

35	Tricalcium phosphate	51.8
	Propylene Glycol	40.0
	F-1	5.5
	Sodium Lauryl Sulphate	1.8
	Flavoring	0.9
40		-----
		100.00

- 56 -

CLAIMS:

1. A cosmetic composition comprising a graft or block copolymer of the formula



wherein G_5 represent monovalent moieties which can independently be the same or different selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, fluoroalkyl, hydrogen, and -ZSA;

A represents a vinyl polymeric segment consisting essentially of polymerized free radically polymerizable monomer,

Z is a divalent linking group,

G_6 represents monovalent moieties which can independently be the same or different selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, fluoroalkyl, hydrogen, and -ZSA;

G_2 comprises A;

G_4 comprises A;

R_1 represents monovalent moieties which can independently be the same or different and are selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, fluoroalkyl, hydrogen, and hydroxyl;

R_2 can independently be the same or different and represents divalent linking groups;

R_3 represents monovalent moieties which can independently be the same or different and are selected from the group consisting of alkyl, aryl, alkaryl, alkoxy, alkylamino, fluoroalkyl, hydrogen, and

- 57 -

hydroxyl;

R_4 can independently be the same or different and are divalent linking groups;

x is an integer of 0-3;

5 y is an integer of 5 or greater;

q is an integer of 0-3;

wherein at least one of the following is true:

q is an integer of at least 1;

x is an integer of at least 1;

10 G_5 comprises at least one -ZSA moiety; and

G_6 comprises at least one -ZSA moiety.

2. The composition of claim 1, wherein R_1 is selected from the group consisting of C_{1-4} alkyl and hydroxyl.

15

3. The composition of claim 1, wherein R_2 is selected from the group consisting of C_1 to C_{10} alkylene, arylene, alkarylene, and alkoxyalkylene.

20 4. The composition of claim 1, wherein R_3 is selected from the group consisting of C_{1-4} alkyl and hydroxyl.

5. The composition of claim 1, wherein R_4 is selected from the group consisting of C_1 to C_{10} alkylene, arylene, 25 alkarylene and alkoxyalkylene.

6. The composition of claim 1, wherein Z is selected from the group consisting of C_1 to C_{10} alkylene, alkarylene, arylene, and alkoxyalkylene.

30

7. The composition of claim 1, wherein G_5 is selected from the group consisting of C_{1-3} alkyl, fluoroalkyl, and phenyl.

35 8. The composition of claim 1, wherein G_6 is selected from the group consisting of C_{1-3} alkyl, fluoroalkyl, and phenyl.

- 58 -

9. The composition of claim 1, wherein y is an integer ranging from about 10 to about 270.

10. The composition of claim 1, wherein y is an
5 integer ranging from about 40 to about 270.

11. The composition of claim 1, wherein said composition is a skin cleansing composition.

10 12. The composition of claim 1, wherein said composition is a hair care composition.

13. The composition of claim 12, wherein said composition is a hair conditioning composition.

15

14. The composition of claim 1, wherein said composition is a skin moisturizing composition.

15. The composition of claim 1, wherein said
20 composition is an oral hygiene preparation.

16. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of acrylic acid
25 esters or methacrylic acid esters of alcohols selected from the group consisting of alkyl alcohols having from 1 to 18 carbon atoms.

17. The composition of claim 1, wherein A comprises
30 polymerized free radically polymerizable monomer selected from the group consisting of acrylic acid esters or methacrylic acid esters of alcohols selected from the group consisting of alkyl alcohols having from 1 to 8 carbon atoms.

35

18. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer

- 59 -

selected from the group consisting of
isooctyl(meth)acrylate, lauryl (meth)acrylate,
2-ethylhexyl (meth)acrylate, isononyl (meth)acrylate,
i-pentyl (meth)acrylate, n-butyl (meth)acrylate,
5 i-butyl (meth)acrylate, methyl (meth)acrylate, ethyl
(meth)acrylate, t-butyl(meth)acrylate, stearyl
(meth)acrylate and mixtures thereof.

19. The composition of claim 1, wherein A comprises
10 polymerized free radically polymerizable monomer
selected from the group consisting of hydrophilic
unsaturated monomers of a cationic, anionic, nonionic,
or amphoteric nature.

15 20. The composition of claim 1, wherein A comprises
polymerized free radically polymerizable monomer
selected from the group consisting of acrylic acid,
methacrylic acid, itaconic acid, acrylonitrile,
crotonic acid, acrylamide, N,N-dimethylacrylamide,
20 N-t-butylacrylamide and methacrylonitrile.

21. The composition of claim 1, wherein A comprises
polymerized free radically polymerizable monomer
selected from the group consisting of succinic
25 anhydride, phthalic anhydride, hydroxy ethyl
(meth)acrylate and hydroxy propyl (meth)acrylate.


22. The composition of claim 1, wherein A comprises
polymerized free radically polymerizable monomer
30 selected from the group consisting of poly(styrene),
poly(α -methyl styrene), poly(vinyl toluene), poly(oxy-
alkylene) and polymethyl (meth)acrylate macromonomers.

23. The composition of claim 1, wherein A comprises
35 polymerized free radically polymerizable monomer
selected from the group consisting of acrylic or
methacrylic monomers having at least one highly

- 60 -

polarizing group selected from the group consisting of hydroxyl, amino (primary, secondary, and tertiary), and ionic groups.


- 5 24. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of monomers represented by the formula:



where $\text{R}^2 = \text{H}$, methyl, ethyl, cyano or carboxymethyl, $\text{L} = -\text{O}$, $-\text{NH}$, $d = 1-3$ and R^3 is a hydrocarbyl radical of valence $d+1$ containing from 1 to 12 carbon atoms.

- 15 25. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate,
20 hydroxybutyl (meth)acrylate, glycerol mono(meth)acrylate, tris(hydroxymethyl) ethane monoacrylate, pentaerythritol mono(meth)acrylate, N-hydroxymethyl (meth)acrylamide, hydroxyethyl (meth)acrylamide and hydroxypropyl (meth)acrylamide.

- 25 26. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of monomers of the formula:



where $\text{R}^2 = \text{H}$, methyl, ethyl, cyano or carboxymethyl,

35 $\text{L} = -\text{O}$, $-\text{NH}$,

$d = 1-3$,


R^3 is a hydrocarbyl radical of valence $d+1$ containing from 1 to 12 carbon atoms,

- 61 -

and R^4 and R^5 are H or alkyl groups of 1 to 12 carbon atoms or together constitute a carbocyclic or heterocyclic group.

- 5 27. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of aminoethyl (meth)acrylate, aminopropyl (meth)acrylate, N,N-dimethylaminoethyl (meth)acrylate,
 10 N,N-diethylaminoethyl (meth)acrylate, N,N-dimethylaminopropyl (meth)acrylamide, N-isopropylaminopropyl (meth)acrylamide, and 4-methyl-1-acryloyl-piperazine.

- 15 28. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of monomers of the formula:



where $R^2 = H, \text{ methyl, ethyl, cyano or carboxymethyl,}$
 25

$L = -O, -NH,$

$d = 1-3,$

R^3 is a hydrocarbyl radical of valence $d+1$ containing from 1 to 12 carbon atoms,

30 and R^4 and R^5 are H or alkyl groups of 1 to 12 carbon atoms or together constitute a carbocyclic or heterocyclic group,

R^6 is H or alkyl group of 1-12 carbon atoms, and Q^- is an organic or inorganic anion.

35

29. The composition of claim 1, wherein A comprises polymerized free radically polymerizable monomer selected from the group consisting of

- 62 -

2-N,N,N-trimethylammoniumethyl (meth)acrylate,
2-N,N,N-triethylammonium ethyl (meth)acrylate,
3-N,N,N-triethylammonium propyl (meth)acrylate,
N(2-N',N',N'-trimethylammonium) ethyl (meth)acrylamide
5 and N-(dimethylhydroxyethylammonium) propyl
(meth)acrylamide.

30. The composition of claim 29, wherein the
counterion is selected from the group consisting of
10 chloride, bromide, acetate, propionate, laurate,
palmitate and stearate.

31. The composition of claim 1, wherein A comprises
polymerized free radically polymerizable monomer
15 selected from the group consisting of methoxyethyl
(meth)acrylate, 2(2-ethoxyethoxy)ethyl (meth)acrylate,
polyethylene glycol mono(meth)acrylate and
polypropylene glycol mono(meth)acrylate.

20 32. The composition of claim 1, wherein A comprises
polymerized free radically polymerizable monomer
selected from the group consisting of vinyl sulphonic
acid, styrene sulphonic acid, 2-acrylamido-2-methyl
propane sulphonic acid and allyloxybenzene sulphonic
25 acid.

33. The composition of claim 1, wherein A comprises
polymerized free radically polymerizable monomer
selected from the group consisting of vinyl pyridines,
30 vinyl imidazoles, vinyl benzimidazoles, vinyl
azlactones, N-vinyl pyrrolidones and vinyl furans.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/04422

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 A61K7/48; A61K7/06; A61K7/16		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	A61K ; C08F	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ^o	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
A	EP,A,0 412 770 (MINNESOTA MINING AND MANUFACTURING COMPANY) 13 February 1991 see the whole document ---	1, 11-14
A	EP,A,0 412 710 (THE PROCTER & GAMBLE COMPANY) 13 February 1991 see the whole document ---	1-14, 16-33
A	EP,A,0 412 704 (THE PROCTER & GAMBLE COMPANY) 13 February 1991 cited in the application see the whole document ---	1-10, 12, 13, 16-33
-/--		
^o Special categories of cited documents : ¹⁰ "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
12 AUGUST 1993	20/8/93	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	COUCKUYT P.J.R.	

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category °	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP,A,0 421 588 (MINNESOTA MINING AND MANUFACTURING COMPANY) 10 April 1991 cited in the application see the whole document ----	1-10, 16-33
A	DATABASE WPI Week 3383, Derwent Publications Ltd., London, GB; AN 83-737364 & JP,A,58 113 300 (LION CORP.) 6 July 1983 see abstract -----	1,12,13

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9304422
SA 74281

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 12/08/93

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP-A-0412770	13-02-91	US-A-	4981903	01-01-91
		AU-A-	5918990	07-02-91
		CA-A-	2021570	08-02-91
		JP-A-	3081311	05-04-91
		US-A-	5021477	04-06-91

EP-A-0412710	13-02-91	US-A-	5106609	21-04-92
		AU-A-	6015990	07-02-91
		JP-A-	3218306	25-09-91
		CN-A-	1056051	13-11-91

EP-A-0412704	13-02-91	AU-B-	624014	28-05-92
		AU-A-	6015890	07-02-91
		CA-A-	2022467	08-02-91
		CN-A-	1049784	13-03-91
		JP-A-	3128311	31-05-91

EP-A-0421588	10-04-91	US-A-	5032460	16-07-91
		JP-A-	3088815	15-04-91
		US-A-	5202190	13-04-93
